

Unclassified

ENV/EPOC/WPRPW(2013)2/FINAL

Organisation de Coopération et de Développement Économiques
Organisation for Economic Co-operation and Development

30-Oct-2015

English - Or. English

ENVIRONMENT DIRECTORATE
ENVIRONMENT POLICY COMMITTEE

Working Party on Resource Productivity and Waste

RECYCLING OF WASTE CONTAINING NANOMATERIALS

Contact: Shunta YAMAGUCHI; Email: Shunta.Yamaguchi@oecd.org; Tel.: +33-1 45 24 84 99

JT03385438

Complete document available on OLIS in its original format

This document and any map included herein are without prejudice to the status of or sovereignty over any territory, to the delimitation of international frontiers and boundaries and to the name of any territory, city or area.



ENV/EPOC/WPRPW(2013)2/FINAL
Unclassified

English - Or. English

TABLE OF CONTENTS

RECYCLING OF WASTE CONTAINING NANOMATERIALS (WCNM).....	3
1. Introduction.....	3
2. The Importance of recycling in waste management	3
3. Key nanomaterials in products.....	4
4. Fate of nanomaterials in recycling operations and potential exposure	5
5. Risks related to nanomaterial in waste.....	6
6. Recycling procedures and Best Available Techniques (BAT)	7
7. Problematic of non-standard treatment of waste.....	8
8. Knowledge gaps and possible activities.....	9
ANNEX.....	12
ACRONYMS AND ABBREVIATIONS.....	14
REFERENCES	15

Tables

Table 1. Summary of reported nanomaterials in WCNM.....	5
Table A1. Selected waste streams with possible WCNM.....	12

RECYCLING OF WASTE CONTAINING NANOMATERIALS (WCNM)

1. Introduction

Today, the number of new commercial products containing nanomaterials is growing (PEN 2013). Many such products are in the personal care/cosmetics/sunscreen categories. The unused leftovers and their packaging, as well as other products containing nanomaterials - such as electronic equipment, textiles or composite plastics - end their life cycle as municipal or industrial waste. They are disposed of by recycling, energy recovery, waste incineration or landfill, as defined in the hierarchy of disposal options. Recycling in general has a higher priority than incineration and/or landfill (EU, 2008), (OECD, 2004/2007).

Today, products containing nanomaterials are being recycled along with their analogous products without nanomaterials. No separation or separate collection of product containing nanomaterials solely due to their nanomaterial-content is known. Also, the existing recycling techniques do not take into account the possible nanospecific risks coming from waste containing nanomaterials.

Recycling operations are not always carried out with techniques that meet the standards of an environmentally sound waste management, with the associated risks for health, safety and environment, even with products that do not (or not yet) contain nanomaterials. If operations are not managed to environmentally sound waste management standards, this may give rise to a lot of potential other problems.

The main objective of this 'Reflection Paper' is to review the current state of knowledge on the fate of nanomaterials in the course of recycling operations and identify the areas where further work on the environmentally sound management of waste containing nanomaterials (WCMN) would be needed.

The paper explains the importance of recycling in waste management in section 2, identifies key nanomaterials in section 3 and investigates the fate of nanomaterials in section 4. The document also explores the risks related to nanomaterials in waste in section 5, covers best available techniques (BAT) and issues of non-standard treatment of waste in section 6 and 7 respectively, and identifies key knowledge gaps and possible areas for further research in section 8.

2. The Importance of recycling in waste management

Recycling of waste is one element in strategies of waste minimisation or waste prevention (OECD, 2000) and of sustainable materials management SMM (OECD, 2012). Individual countries and international bodies are setting recycling goals and are taking measures to reach them. In the EU, several legal provisions exist with obligation for the member states (EU, 2008), (EEA, 2013) to recycle municipal waste and/or household waste. In the United States, the Environmental Protection Agency (EPA) regulates household, industrial, manufacturing and commercial solid and hazardous wastes under the Resource Conservation and Recovery Act (RCRA). Effective solid waste management is a cooperative effort involving federal, state, regional, and local entities.

In the OECD, the average recycling rate (including composting) for municipal waste was estimated at 33% in 2011, with a range from less than 10 per cent to 63 per cent (OECD Statistics¹). In the EU, the overall rate of material recovery (recycling plus composting) amounts to 42%, the range in individual countries is given as going from 2% to 70% (EUROSTAT, 2011).

Based on different sources, the main waste streams recycled in municipal and industrial waste are listed below [(EIONET, 2010), (US-EPA, 2013), (FOEN, 2012), (OECD Statistics)]. In addition, there is a growing interest of the recycling industry to recover metals and mineral secondary raw materials from bottom ash ('slag') of Municipal Solid Waste Incinerators MSWI (Boeni, 2013). This waste stream is also included in the following list:

- ✓ Bio waste
- ✓ Food Waste
- ✓ Glass (bottles)
- ✓ Metal
- ✓ Paper and cardboard
- ✓ Plastic (PET and various other plastics)
- ✓ Leather and Textiles
- ✓ Waste of Electronic and Electrical Equipment WEEE
- ✓ Batteries
- ✓ Wood
- ✓ Construction and Demolition Wastes
- ✓ End of Life Vehicles ELV:
- ✓ Tires
- ✓ Recycling of residues from waste incineration plants (recovery of metals from bottom ash by mechanical separation or from fly ash by acid washing)

Processes where nano-related waste streams can be generated include production, distribution, handling (and use) as well as disposal (NIEPH, 2011). It is anticipated that, as the production and number of nanomaterial applications increase, waste streams containing nanomaterials will also increase, and in addition to naturally occurring nanoparticles, engineered nanomaterials possibly might become more widespread in the environment, if insufficient knowledge about the fate and associated risks of nanomaterials released from waste treatment operations, as recycling, could result in inadequate management.

3. Key nanomaterials in products

When discussing the problem of recycling of WCNM, some product categories are particularly significant as potentially ENM-containing products and thus leading to WCNM. From different sources, Nanomaterial containing products and nanomaterial types have been compiled in (Struwe *et al.*, 2012), PEN 2013 (The Project on Emerging Nanotechnology)², for consumer products, (Lee, 2010) and (ITA-AAS, 2012) for construction material and (NIEPH, 2011) on the use of nanomaterials in composite plastics ("Nanocomposites").

¹ OECD Statistics <http://stats.oecd.org/Index.aspx?DataSetCode=WASTE>

² PEN The Project on Emerging Nanotechnologies: www.nanotechproject.org/inventories/consumer/analysis_draft (retrieved Aug 16, 2013).

Table 1 provides a list of nanomaterials which may be contained in consumer products, with specific examples.

Table 1. Summary of reported nanomaterials in WCNM

Nanomaterial	Consumer Products (Struwe <i>et al.</i> 2012) (PEN 2013) (NEEPH 2011)	Construction Material (Lee 2010) (ITA-AAS 2012)
<i>Carbon Nanotubes CNT</i>	Electronic devices, sports equipment, composite plastics	Concrete, ceramics
<i>Fullerene</i>	Semi-conductor technology	
<i>nano-Silver (nAg)</i>	Textiles, anti-bacterial kitchenware	Antibacterial coatings and paints
<i>Carbon Black (CB)</i>	Tires, printing toner, plastics	
<i>nano Titanium dioxide (nTiO₂)</i>	Paints, coatings, composite plastics	Self-cleaning coatings
<i>nano Silicon dioxide (amorphous and crystalline nSiO₂)</i>	Coatings, composite plastics, tires,	Concrete, ceramics, window coatings
<i>nano Zinc oxide (nZnO)</i>	cosmetics, coatings and paints,	
<i>nano Titanium nitride (nTiN)</i>	PET-bottles	
<i>nano Iron oxides (n FeO/Fe₂O₃)</i>	Electronic devices	Concrete
<i>Nano Ceriumoxide (nCeO₂)</i>	Fuel additive	Anti-corrosive coatings
<i>Nano Phosphate ® (nLiFePO₄)³</i>	Li-Batteries	
<i>Nano Copper particles (nCu)</i>		improved steel (anticorrosive)

4. Fate of nanomaterials in recycling operations and potential exposure

Waste recycling has many facets: there is a wide variety of recyclable materials within a waste stream; there are various recycling methods, more or less technically adapted to the specific waste stream and/or secondary raw material to be recovered. The appendix to this paper includes a table listing some waste streams with possible WCNM, a short description of recycling procedures, and known nanomaterials.

The main concern about possible nanospecific risks of WCNM in recycling processes are nano-objects that might be released into the workplace atmosphere, or into the environment by way of the air, water and or soil (Struwe *et al.*, 2012) (NEEPH, 2011) (FOEN, 2010).

Information about the fate of nanomaterials in recycling processes is only beginning to emerge. Mostly, exposure scenarios are based on modelling, and not on evidence. It is extremely difficult to quantify and monitor the long-term release of ENM during the final disposal of ENM containing products. (Gottschalk & Nowack, 2011). A “Tiered Approach to an Exposure Measurement and Assessment of Nanoscale Aerosols Released from Engineered Nanomaterials in Workplace Operations” has been

³ http://en.wikipedia.org/wiki/Lithium_iron_phosphate#The_Physical_and_Chemical_Properties_of_LFP

proposed by a group of several German institutes (Tiered Approach, 2011), which may give guidance in assessing also the release of ENMs during recycling operations.

Potential risks of exposure depend on the specific recycling processes to which the WCNM is subject. Shredding, milling and thermal processing may result in high exposure potentials, if not operated in enclosed processes. If filters are not designed for nanoparticles, there may be exhaust to the environment. Manual dismantling may cause release of nano-objects and direct exposure of workers. (Koehler *et al.*, 2008). A transfer of unwanted or even detrimental nanomaterials to recycled materials ("cross-contamination") may occur and may possibly be detrimental to the quality of the recycled materials (Chaudhry *et al.*, 2009).

5. Risks related to nanomaterial in waste

During the recycling of Waste Containing Nanomaterials, engineered nanoparticles, like any other particle in the recycling process, might remain individually isolated or form new bigger agglomerates. Nanorelevant potential exposure exists mainly in connection with free nano-objects that are in the nanoscale (smaller than 100 nm) in all three or in two spatial dimensions (nanoparticles, nanofibers, nanorods) (British Standards, 2007):

- Nanoparticles may penetrate biological barriers.
- They may show intensified effects in the case of substances with toxic properties.
- They may have increased bioavailability.
- They may have different chemical and physical properties from the "parent" material.
- Some types of CNT (carbon nanotubes) and nanowires may have similar effects in the lungs to asbestos fibres.
- Attention must be paid to the risk of dust explosions (as in all applications of inflammable powders or powdery substances).

These possible exposures must be taken into account when managing waste containing nanomaterials, especially nano-objects that are free or that are releasable (e.g. due to the recycling process). Guidance for the safe recovery and disposal of waste containing nanomaterials has been given for example in (VCI, 2012).

Much research has been done and is still done on health, safety and environment impacts of nanomaterials and on their toxicology and ecotoxicology (JRC/ESAC 2011, Danish EPA, 2011). *'Health and environmental hazards have been demonstrated for a variety of manufactured nanomaterials'*, however *"Not all nanomaterials induce toxic effects. Some manufactured nanomaterials have already been in use for a long time (e.g. carbon black, TiO₂) showing low toxicity. Therefore, the hypothesis that smaller means more reactive, and thus more toxic, cannot be substantiated by the published data. In this respect, nanomaterials are similar to normal chemicals/substances in that some may be toxic and some may not. As there is not yet a generally applicable paradigm for nanomaterial hazard identification, a case-by-case approach for the risk assessment of nanomaterials is still recommended."*(SCENHIR, 2009)

The wide variety of consumer products makes it difficult to devise and verify a generic exposure assessment and risk management for nanoproducts as a class (JRC/ESAC, 2011). Publications which address the risk-potential associated with consumer products when they enter the recycling process are found in (Struwe *et al.*, 2012; Ostertag & Huesing, 2007; Kuhlbusch & Nickel, 2010). Examples of studies

on specific nanomaterials are (Burkhardt, 2011) on Silver, (Nanosustain⁴) on ZnO and Nanocellulose, (Danish EPA, 2011) on Titanium dioxide; Cerium dioxide; Fullerenes (Carbon balls); Silver; Zero-valent iron; Silicon dioxide and Nanoclay.

There is still uncertainty about the effective nano-specific risks of ENM in recycled waste streams containing nanomaterials, because there exist no or only a few studies. In the best case, the data are just sufficient to make a preliminary assessment (Struwe *et al.*, 2012). Examples are risks coming from carbon nanotubes which, due to their specific form, may show cancerogenic effects in the lung. Nanosilver is used in textiles and other products because of its biocide (antibacterial) properties, which may bring a risk potential if free nanosilver reaches the environment.

The potential risk of a specific ENM in a waste stream is not only a function of the toxicity or ecotoxicity of the nanomaterial. Additional factors may determine the risk potential of a nanomaterial during recycling, and further research is needed to clarify these issues:

- Quantity / concentration of the ENM in the product or in the waste stream.
- The mode of incorporation of ENM in the product: Are they in a free form, associated with other materials, or fixed by chemical binding?
- Will the ENM be set free with a specific recycling operation?
- Will free ENM stay as single nanoparticles or nanorods or will they agglomerate to bigger entities?
- Will secondary materials (e.g. plastics or construction materials) produced from recycling processes be contaminated in an uncontrolled manner by the ENM enclosed in the original products containing nanomaterials (cross-contamination) which have been recycled?

However, there is enough uncertainty and suspicion of harm to invoke preventive measures (FOEN, 2010; Japan Ministry of Environment, 2009; BSI, 2007; VDI, 2004) against the potential nanospecific risks for health or environment during recycling of waste containing nanomaterial.

6. Recycling procedures and Best Available Techniques (BAT)

Recycling operations shall be done in an environmentally sound manner, according to the Best Available Techniques and by the Best Environmental Practices (BAT/BEP) (OECD, 2004/2007; OECD, 2007); (EU, 2008). The EU proposes *the integration of assessment of risk to human health, the environment, consumers and workers at all stages of the life cycle of the technology (including conception, R&D, manufacturing, distribution, use and disposal)* (EU, 2004). In view of the uncertainties concerning the fate of nanomaterials during recycling processes, this may also be useful as a precautionary measure to mitigate possible exposure to ENM.

During recycling operations, the main possibilities of exposure to nanomaterials in the recycling process of waste streams that may contain WCNM may be (Struwe *et al.*, 2012).

Exposure to fine or ultrafine dust containing free nano-objects emitted during transport, sorting, shredding, grinding or pouring of the WCNM.

⁴ www.nanosustain.eu/component/content/article/1-latest-news/128-nanosustain-factsheet-and-case-studies

Exposure to nano-objects in liquid media (water, solvents) due to cleaning or rinsing the products before mechanical recycling; also exposure to contact with nano objects on cleaning clothes from maintenance and cleaning of recycling equipment.

Exposure to nano-objects that may be set free in the flue gas or to the ambient air with thermal processes (heating, welding, pyrolysis) when there is insufficient occupational control.

If by an assessment of possible risks it is known or suspected that nanoparticles are released during production, handling or further processing, workers' exposure to ENMs can be prevented by taking the following safety measures by this order of priority (VDI, 2004; BSI, 2007; Japan Ministry of Environment, 2009; FOEN, 2010; VCI/BAuA, 2012; BAuA, 2013).

- 1) Technical measures at the source, e.g. use of hermetically sealed apparatus; minimisation of dusts and aerosols; extraction of dusts and aerosols directly at the source; filtering of extracted air, if necessary isolation of the workroom and appropriate modification of room ventilation; cleaning of recycling equipment by vacuum cleaning with suitable appliances or wiping with a damp cloth, but not by blowing off.
- 2) Organisational measures, e.g. minimisation of the exposure time; minimisation of the number of persons exposed; restriction of access; instructions of personnel concerning hazards and protection measures.
- 3) Personal protective measures: respiratory protection with particle filters P3; protection gloves; closed goggles; protection suit (non-woven).

Recommendations and guidelines on safe management of engineered nanomaterials have been published by several public and private organisations (e.g. VDI, 2004; BSI, 2007; FOEN, 2010; Japan Ministry of Environment, 2009; NEEPH, 2011), and the OECD recommendation [C\(2004\)100](#) on Environmentally Sound Management of waste (OECD, 2004/2007) includes exposure prevention measures.

7. Problematic of non-standard treatment of waste

Struwe *et al.* (2012) distinguish between two categories of recycled WCNM:

- a) WCNM with heterogeneous composition, containing different products in their waste stream. Additionally, the different products also contain multiple diverse nanomaterials, often not even known. This category includes for example WEEE, end-of-life vehicles, paper and most plastic waste.
- b) WCNM with comparatively homogeneous composition, containing only few, normally known nanomaterials, e.g. PET-bottles, used tires, Li-ion batteries.

It seems reasonable to assume that emission control with WCNM of the first category will pose more difficulties, because of the diversity of products and nanomaterials and/or the complexity of the recycling technique (e.g. with WEEE, ELV or CDW).

We can suppose that the application of known techniques for workers and environment protection would also in a general way decrease the risk, when there are nanomaterials in the waste stream (Japan Ministry of Environment, 2009; FOEN, 2010; NEEPH, 2011; SRU, 2011; Struwe *et al.*, 2012; Boeni, 2013).

By applying appropriate BAT procedures for waste treatment,⁵ emissions in general will be lowered, and it can be expected that possible exposure to ENM will also be lowered. The following list gives a short selection of elements mentioned in the cited document that may be considered as BAT when handling waste:

- Environment Management System in order to know the processes, the accepted waste and the waste and secondary products going out of the treatment installation;
- ensure proper location and drainage of storage facilities;
- unloading solids and sludge in closed areas;
- perform crushing/shredding and sieving operations in areas fitted with fitted with extractive vent systems linked to abatement equipment when handling materials that can generate emission to air (e.g. Odours, dust, vocs);
- proper management of waste water from the treatment plant;
- air emission treatment;
- management of process residues;
- avoid soil contamination.

The following statement made by the British Health and Safety Executive about BAT/BEP to apply with WEEE-Recycling does not refer to WCNM, but to substances like mercury or lead. However, The principle formulated here may - 'mutatis mutandis' - give good guidance when implementing BAT in recycling technologies where there is to expect WCNM in the waste stream:

“As a result of this complex mix of product types and materials, some of which are hazardous (including arsenic, cadmium, lead and mercury and certain flame retardants) WEEE recycling poses a number of health risks that need to be adequately managed. For example, exposure to substances released during processing (such as mercury released from fluorescent tubes, lead and phosphorous pentachloride as a result of breaking cathode ray tubes). **It is important to stress that if effective measures are taken to control exposure to mercury and lead, then normally the control of exposure to other hazardous substances should also be adequate**”.⁶

This adequacy is true when releases and exposures to the nanomaterials may occur in the same recycling process steps that are specifically controlled to reduce or eliminate releases and exposures to mercury and lead.

8. Knowledge gaps and possible activities

The principal challenges with safe and environmentally sound recycling procedures for waste containing nanomaterials are:

- a) controlling the health, safety and environmental risks arising from recycling processes of waste containing nanomaterials;

⁵ For guidance on the implementation of BAT in the waste sector, see EU/IPPC-Document on Best Available Techniques for the Waste Treatment Industries (EU-IPPC, 2006, <http://eippcb.jrc.ec.europa.eu/reference/>), even if it is not mentioning Waste Containing Nanomaterial at all.

⁶ UK Health and Safety Executive www.hse.gov.uk/waste/waste-electrical.htm

- b) controlling the technical and environmental quality of secondary materials that may be contaminated with ENM from the original waste stream;
- c) developing technologies that may be used for the recovery of the ENM from the products, given suitable quantities, concentrations and economic value of the ENMs.

Several authors who have identified knowledge gaps in the context of recycling of WCNM recommend actions that can be taken in order to improve the current uncertainty (Japan Ministry of Environment, 2009; Struwe *et al.*, 2012; NEEPH, 2011; Gottschalk & Nowack, 2011; Kuhlbusch & Nickel, 2010; FOEN, 2010; Lee, 2010). From these statements, the most important knowledge gaps and proposed measures in the context of recycling of WCNM can be summarised as follows:

Knowledge gaps and open questions	Possible activities
Types and quantities of nanomaterials in products and waste and associated risk potentials?	<ul style="list-style-type: none"> • Evaluation of types and quantities of specific nano-materials in waste streams • Labelling of products containing nanomaterials • Produce experimental and analytical data about the main release sources during all ENM life stages: ENM production, manufacturing of nanoproducts, consumption and disposal of nanoproducts.
Behaviour and fate of the nanomaterials in products during the recycling processes (from collection to the preparation of the recycled products): do they stay in the material, are they set free and if so, are they in a form that is a risk for health, safety and environment (HSE)?	<ul style="list-style-type: none"> • Research on the risk of release of NPR from composite products during waste treatment (e.g. with shredding) • Produce experimental and analytical data regarding the form the ENM are released, such as whether the ENM are agglomerated or present as single particles or if they are embedded within a matrix • Additional research on the possibilities that nanomaterials from WCNM 'diluted' to other materials during the recycling procedure may impair the quality of these materials
The most suitable technologies for emission control and for protection of humans and the environment when recycling WCNM?	<ul style="list-style-type: none"> • Identification of possible sources of ENM emissions and of the concerned workplaces in the recycling industry • Preventive measures on the basis of existing guidelines and knowledge for health protection and workplace safety • Research on the effectiveness of the current waste management systems' suitability of dealing with new pollutants containing nanoscaled structures • Implementation of preventive measures on the basis of existing guidelines and knowledge for health protection and workplace safety • Development of dedicated guidelines for the recycling industry
Measurement and identification of ENM in products and waste streams	<ul style="list-style-type: none"> • Development of methods and standardisation of "emission measurements" with examination of the relevant parameters with respect to norms.

Knowledge gaps and open questions	Possible activities
Effects of cross-contamination of recycled materials with nanomaterials from WCNM	<ul style="list-style-type: none"> • Additional research on the possibilities that nanomaterials from WCNM may be 'diluted' to other, downcycled materials during the recycling procedure • Research on how far nanomaterials can interfere with or prevent recycling and recovery
Possibility of recovery of nanomaterials from a waste stream	<ul style="list-style-type: none"> • Evaluation of eventual need for separate collection for specific types of waste containing nanomaterials, for example because of the quantities expected or because they are hazardous.

ANNEX

Table A1. Selected waste streams with possible WCNM

Waste type	Recycling procedure	Nanomaterials	Theoretically possible sources of nano object emissions in the recycling process
Metal waste (scrap)	Shredding, smelting	In coatings: Metal oxides, CNT, SiO ₂	Shredding, if ENM can be set free from coatings Smelting: ENM that are not destroyed in the melting process, insufficient exhaust gas purification
Paper and cardboard	Pulping, de-inking (wet processes) www.paperonline.org/environment/paper-recycling/the-paper-recycling-process	Carbon Black (from the ink), TiO ₂ (except for special papers, TiO ₂ is not in the nano-form)	Dust from collection, transport Aerosols of ink from pulping and de-inking
Plastic	Collect & sorting, or separate collection (e.g. for PET-bottles) mechanical recycling: shredding, washing, regranulation Feedstock recycling: depolymerisation, cracking (for basic chemicals)	CNT, SiO ₂ , TiO ₂	Shredding and regranulation: if nano objects are set free. Feedstock (chemical) recycling: nano objects that are not destroyed in the process may be emitted or end up in the cracking residues (tar). Problem of dispersion of ENM to regranulated plastics
Textiles	Collect, reuse, sorting, preparing for reuse, shredding to get fibres	CNT, Ag	Shredding: if nano objects are set free
Waste of Electronic and Electrical Equipment WEEE	Collect, dismantling, sorting by hand, shredding and separation of the fractions, processing of fractions (non-magnetic metals, iron, glass, plastics etc.), further processing of the components (metal melting, material recovery of iron and non-iron metals, extraction of metals from circuit boards)	Carbon black (in plastic and in toners), CNT (in electronic devices and in plastic housings, nano-Iron oxide, ZnO, SiO ₂ , Ag (in coatings)	Any step of the procedure, depending on the nanomaterial containing component and on the specific type of nanomaterial.
Batteries	Collect, sorting. Mechanical/chemical and/or thermal treatment (various procedures, e.g. BATREC (Switzerland) ⁷ for alkali- and mercury batteries, Battery Solutions (USA) ⁸ , Toxco (USA) ⁹ for lithium batteries, or INMETCO (USA) for Ni-Cd Batteries ¹⁰ . Another informative and educative website: ¹¹ http://batteryuniversity.com/learn/article/recycling_batteries	Electrodes with CNT or Nano-Phosphate® (nLiFePO ₄) ¹²	In principle during mechanical, chemical or thermal treatment, dependent on the process and on the type of battery with nanomaterial.

⁷ BATREC Industries AG, in Wimmis, Switzerland: www.batrec.ch/en-us/unsere_angebot/batterien/recyclingprozess.html# (accessed Aug. 28, 2013)

⁸ www.batteryrecycling.com/Battery+Recycling+Process (accessed Aug. 28, 2013)

⁹ Toxco Recycling Processes, www.toxco.com/processes.html (accessed Aug.28, 2013)

Waste type	Recycling procedure	Nanomaterials	Theoretically possible sources of nano object emissions in the recycling process
Construction and Demolition Wastes.	Reuse of components, sorting of fractions (wood, concrete, brick, metal etc.), metal recycling, secondary building materials, incineration and landfill	CNT, SiO ₂ , TiO ₂ , Fe ₂ O ₃ , Cu, Ag	During destruction of buildings (dust emissions), shredding, grinding if nano objects are set free. Problem of dispersion of ENM fractions of recycled material
End of Life Vehicles (ELV)	Dismantling for reusable parts (incl. tires), removal of hazardous components (e.g. batteries), shredding and separation of fractions, metals go to smelting and refining, glass is recycled or landfilled, non-metallic shredder residues for incineration or landfill (Ostertag & Huesing, 2007)	CNT, SiO ₂ , TiO ₂ (in plastics, coatings and paints)	Shredding and sorting of fractions, smelting of metals (ENM from coatings), disposal of non-metallic shredder fraction. Modern cars contain electronic components that are normally not removed before shredding, this is a possible source for ENM-emissions
Tires	Collect, storage (danger of ignition), refurbish and reuse, shredding, of metal, reuse of rubber for downcycled products or for energy recovery (according to www.amni.de/de/anlagen/reifenrecycling.html) 27% of tires worldwide were recycled 2005, only 6% in 1995; landfill dropped from 62% to 22 % in the same time) Information on Scrap Tires and environmental issues in: http://en.wikipedia.org/wiki/Rubber_tires#Rubber_tires	Carbon Black, silica; there are indications that future developments will include others, e.g. CNT, nanoclay (SiO ₂) or organic nano-Polymers (ObservatoryNANO 2011)	In principle when shredding, actual tires contain ENMs that are bound to the rubber matrix (Peters 2012)
Recycling of residues from waste incineration:	separation of metals bottom ash from MSWI, (ca. 220 kg of Bottom ash are produced when incinerating 1 ton of MSW, these contain metal residues (Iron, Aluminium, Copper, even Gold) from MSW. (FOEN, 2007, Boeni, 2013)	ENM from WCNM in the municipal waste that are not destroyed or evaporated may stay in the bottom ash. -	The most efficient recovery of metals from bottom ash is done with dry ash, with dust generation: nano objects can be emitted during pouring, sieving, mechanical and magnetic separation

Source: Compiled by authors from sources already cited.

¹⁰ www.inmetco.com/services_battery.htm

¹¹ The Battery University, private project of a former Swiss, now Canadian entrepreneur, founder of CADEX Electronics http://batteryuniversity.com/learn/article/recycling_batteries (accessed Aug. 28, 2013)

¹² http://en.wikipedia.org/wiki/Lithium_iron_phosphate#The_Physical_and_Chemical_Properties_of_LFP

ACRONYMS AND ABBREVIATIONS

BAT	Best Available Technology
BEP	Best Environment Procedure
CeO ₂	Cerium-Dioxide
CNT	Carbon Nanotubes
EEA	European Environment Agency
EIONET	European Environment Information and Observation Network
ELV	End of Life Vehicles
ENM	Engineered Nanomaterials, see also MNM
EPA	US Environment Protection Agency
ESAC	European Centre for the Validation of Alternative Methods Scientific Advisory Committee
ESM	Environmentally Sound Management
EU	European Union
EU FP7	European Union Seventh Framework Program (R+D)
EUROSTAT	Statistical Office of the European Communities
FOEN	Swiss Federal Office for the Environment
FOPH	Swiss Federal Office for Public Health
ITA-AAS	Institute for Technology Assessment-Austrian Academy of Sciences
JRC	Joint Research Centre of the EU in Ispra (Italy)
MNM	Manufactured Nanomaterials
MSW	Municipal Solid Waste
MSWI	Municipal Solid Waste Incinerator
MWCNT	Multi Wall Carbon Nanotubes
nAg	nano-Silver
NEEPH	Nanomaterials Related Environmental Pollution And Health Hazards Throughout Their Life-Cycle (EU FP7)
NM	Nanomaterials
NP	Nanoparticles
PEN	The Project on Emerging Nanotechnologies
PPC	Pollution Prevention and Control
RCRA	US Resource Conservation and Recovery Act
REACH	EU Regulation for Registration, Evaluation, Authorisation and Restriction of Chemicals
ROS	Reactive Oxygen Species
SECO	Swiss State Secretariat for Economic Affairs
SiO ₂	Silica, Silicium-Dioxide
SMM	Sustainable Materials Management
SWCNT	Single Wall Carbon Nanotubes
TiN	Titanium-Nitride
TiO ₂	Titanium-Dioxide
WCNM	Waste containing nanomaterials
WEEE	Waste of Electronic and Electrical Equipment
ZnO	Zinc-Oxide

REFERENCES

- BAuA (2013), German Federal Institute for Occupational Safety and Health (BAuA), Committee on Hazardous Substances (AGS), *Announcement on Hazardous Substances, Manufactured Nanomaterials*, Announcement 527, Berlin
www.baua.de/en/Topics-from-A-to-Z/Hazardous-Substances/TRGS/Announcement-527.html
- BIO Intelligence Service (2011), Mudgal, Sh. *et al.*, *Study on Coherence of Waste Legislation*, Final Report prepared for the European Commission (DG ENV), Paris
- Boeni, L. (2013), *Accumulation of Recovered Gold from Bottom Ash*, Matriculation Paper, Hinwil (CH);
www.zar-ch.ch/en/home/news/news-en/datum/2013/01/29/maturitaetsarbeit.html
- Burkhardt M., A. Englert, R. Iten, S. Schärer (2011), *HSR Hochschule für Technik Rapperswil*, Institut für Umwelt und Verfahrenstechnik (UMTEC), Rapperswil (CH);
www.bafu.admin.ch/abfall/01472/12850/index.html?lang=en;
- Chaudhry, Q. *et al.* (2009), *Nanolifecycle: A lifecycle assessment study of the route and extent of human exposure via inhalation for commercially available products and applications containing carbon nanotubes*, Food and Environment Research Agency, York, United Kingdom
- Danish EPA (2011), Sonja Hagen Mikkelsen *et al.*, *Survey on basic knowledge about exposure and potential environmental and health risks for selected nanomaterials*; Danish Environment Protection Agency, Environmental Project No. 1370, Copenhagen;
<http://search2.mim.dk/sitesearch/ClickCounter.asp?u=http%3a%2f%2fwww2%2emst%2edk%2fudgiv%2fpublications%2f2011%2f08%2f978%2d87%2d92779%2d09%2d0%2epdf&l=22162773&c=75&s=65&p=1>
- DEFRA (2006), Department for Environment, *Food and Rural Affairs; Guidance on Best Available Treatment Recovery and Recycling Techniques (BATRRRT) and treatment of Waste Electrical and Electronic Equipment*, (WEEE), London
- EEA (2013), Fischer, Chr. *et al.*, *Managing municipal solid waste — a review of achievements in 32 European countries*, European Environment Agency Report No2/2013, Copenhagen
- EIONET (2009), Fischer, Chr. & Werge, Mads, *Europe as a Recycling Society: Present recycling levels of Municipal Waste and Construction & Demolition Waste in the EU*, European Topic Centre on Sustainable Consumption and Production, Copenhagen;
http://scp.eionet.europa.eu/publications/wp2009_2;
- EIONET (2010), Fischer, Chr. & C. Davidsen, *Europe as a Recycling Society: The European Recycling Map*, European Topic Centre on Sustainable Consumption and Production, Copenhagen;
http://scp.eionet.europa.eu/publications/WP2010_5_The%20European%20Recycling%20Map
- EU (2004), European Commission; *Towards a European strategy for nanotechnology*, Brussels;
http://ec.europa.eu/nanotechnology/pdf/nano_com_en_new.pdf
- EU (2008), Directive 2008/98/EC of the European Parliament and of the Council of 19 November 2008 on Waste

- EU/IPPC (2006), IPPC Bureau; *Integrated Pollution Prevention and Control: Reference Document on Best Available Techniques for the Waste Treatment Industries*, Seville;
<http://eippcb.jrc.ec.europa.eu/reference/>
- EUROSTAT (2011), Blumenthal, K.; *Generation and Treatment of Municipal Waste*, EUROSTAT, Statistics in Focus 31/2011, Luxembourg;
http://epp.eurostat.ec.europa.eu/cache/ITY_OFFPUB/KS-SF-11-031/EN/KS-SF-11-031-EN.PDF
- FOEN (2007), Fierz, R. & R. Bunge, *Trockenaustrag von KVA-Schlacke (Dry Discharge of Bottom Ash*, in German), Summary of the project, funded by FOEN, Bern;
https://www.google.ch/url?sa=t&rct=j&q=&esrc=s&source=web&cd=1&ved=0CC0QFjAA&url=http%3A%2F%2Fwww.bafu.admin.ch%2Ffall%2F01495%2F01496%2Findex.html%3Flang%3De%26download%3DNHzLpZeg7t%2CInp6i0NTU042l2Z6lnlacy4Zn4Z2qZpnO2Yuq2Z6gpJCFdIF3gGym162epYbg2c_JjK
- FOEN (2010), Tellenbach-Sommer, M., *Environmentally sound and safe disposal of waste from manufacturing and industrial and commercial processing of synthetic nanomaterials*, Swiss Federal Office for the Environment (FOEN), Bern;
www.bafu.admin.ch/chemikalien/01389/01393/01394/index.html?lang=en;
- FOEN (2012), *Swiss Federal Office for the Environment, Multi Year Waste Statistics, Factsheets*, Bern;
www.bafu.admin.ch/abfall/01517/01519/01524/index.html?lang=en
- Gottschalk & Nowack (2011), F. Gottschalk and B. Nowack, *The release of engineered nanomaterials to the environment*, J. Environ. Monit., 13, 1145-1155, Cambridge
- Hendren *et al.* (2011), Hendren, Chr-O., X. Mesnard, J. Droege, M. Wiesner, *Estimating Production Data for Five Engineered Nanomaterials As a Basis for Exposure Assessment*, Environmental Science & Technology, 48, 2562-2569, ACS Publication
- INRS (2007), Honnert, B., R. Vincent, *Production et utilisation industrielle des particules nanostructurées*, INRS, Département Métrologie des Polluants, Paris;
[www.inrs.fr/accueil/produits/mediatheque/doc/publications.html?refINRS=ND%202277](http://www.inrs.fr/accueil/produits/mediatheque/doc/publications.html?refINRS=ND%202277;);
- ITA-AAS (2012), Gressler, S. & A. Gaszo, *Nano in the Construction Industry*, Nano Trust Dossier No. 32, August, Institute of Technology Assessment of the Austrian Academy of Sciences, Vienna
- ITA-AAS (2012)a, Simko M. & R. Fries, (Nano)-Titanium dioxide (Part III): Environmental effects; Nano Trust Dossier No. 35en, December 2012, Institute of Technology Assessment of the Austrian Academy of Sciences, Vienna, 2012
- Japan, Ministry of Environment (2009), Expert committee on the environmental impact of manufactured nanomaterials, Ministry of the Environment; Guidelines for preventing the environmental impact of manufactured nanomaterials (abstract, tentative translation June 2009), Japan
- JRC/ESAC (2011), Aebi *et al.*, *Impact of Engineered Nanomaterials on Health: Considerations for Benefit-Risk Assessment*, European Commission Joint Research Centre Institute for Health and Consumer Protection (IHCP), Ispra (I);
<http://publications.jrc.ec.europa.eu/repository/handle/111111111/22610>
- Koehler *et al.* (2008), Koehler, A. *et al.*; *CNT in Li-Ion-Batteries and Synthetic Textiles: Studying the potential release of carbon nanotubes throughout the application life cycle*, Journal of Cleaner Production, Volume 16, Issues 8–9, May–June, Pages 927–937
- Kulbusch, Th. & C. Nickel (2010), *Nanoparticle emission of selected products during their life cycle (Emission von Nanopartikeln aus ausgewählten Produkten im Lebenszyklus)*, Institute for Energy and Environmental Technology (IUTA) e. V (funded by German Umweltbundesamt UBA), Duisburg

- Lee, J., S. Mahendra and P. J. J. Alvarez (2010), *Nanomaterials in the Construction Industry: A Review of Their Applications and Environmental Health and Safety Considerations*, ACS Nano, 4 (7), 3580–3590; Washington DC
- NEEPH (2011), EKOTEK, Guidelines for responsible management of waste nanomaterials; EU FP7 NEEPH
- OECD (2000), STRATEGIC WASTE PREVENTION, OECD Reference Manual, [ENV/EPOC/PPC\(2000\)5/FINAL](#), OECD, Paris
- OECD (2004/2007), Recommendation of the Council on the Environmentally Sound Management of Waste, ([C\(2004\)100](#), amended on 16 October 2007 - [C\(2007\)97](#)), OECD Paris; <http://acts.oecd.org/Instruments/ShowInstrumentView.aspx?InstrumentID=51&InstrumentPID=48&Lang=en&Book=False>
- OECD (2007), de Tilly, S. *et al.*, *Guidance Manual for the Implementation of the OECD Recommendation C(2004)100 on Environmentally Sound Management*; OECD; Paris; www.oecd.org/env/waste/39559085.pdf;
- OECD (2012), *Sustainable Materials Management: Making Better Use of Resources*; OECD Publishing; Paris; www.keepeek.com/Digital-Asset-Management/oecd/environment/sustainable-materials-management_9789264174269-en;
- OECD Statistics, OECD; Municipal Waste - Generation and Treatment; OECD Stat, Extracts Website, Paris; <http://stats.oecd.org/Index.aspx?DataSetCode=WASTE>
- Ostertag, K. und B. Huesing (2007), In: Bilitewski, B., Schnurer, H., Zeschmar-Lahl, B. (Eds.): *Müllhandbuch*, 2. Aufl.: 8054.1–8054.27; Erich Schmidt, Berlin
- PEN (2013), *The Project on Emerging Nanotechnologies; Inventories on Consumer Products*, PEN-Website, Washington DC; www.nanotechproject.org/inventories/consumer/analysis_draft/
- Peters, F. (2012), *End-of-life tyres including nanomaterials*, Presentation OECD WPRPW Munich Workshop, May
- Piccinno, F., F. Gottschalk, S. Seeger & B. Nowack (2012), *Industrial production quantities and uses of ten engineered nanomaterials in Europe and the world*, J. Nanopart. Res. (2012)14:1109, Springer
- SCENIHR (2009), Scientific Committee on Emerging and Newly Identified Health Risks, *Risk Assessment of Products of Nanotechnologies*, European Commission, DG Health & Consumers, Brussels http://ec.europa.eu/health/ph_risk/committees/04_scenihr/docs/scenihr_o_023.pdf
- SRU (2011), German Advisory Council on the Environment (Sachverständigenrat für Umweltfragen), *Precautionary Strategies for Managing Nanomaterials (Vorsorgestrategien für Nanomaterialien, Sondergutachten)*, Berlin; www.umweltrat.de/EN/TheGermanAdvisoryCouncilOnTheEnvironment/the_german_advisory_council_on_the_environment_node.html
- Struwe, J. *et al.* (2012), *Bedeutung von Nanomaterialien beim Recycling von Abfällen*, Hans Böckler Stiftung Arbeitspapier AP 270, November
- Swiss Government (2008), *Swiss Government: Action Plan Synthetic Nanomaterials*, Bern; 2008; www.bafu.admin.ch/publikationen/publikation/00574/index.html?lang=en
- Tiered Approach (2011), *Tiered Approach to an Exposure Measurement and Assessment of Nanoscale Aerosols Released from Engineered Nanomaterials in Workplace Operations*, Air Quality and Sustainable Nanotechnology, Institute of Energy and Environmental Technology e. V. (IUTA); Federal Institute for Occupational Safety and Health (BAuA); German Social Accident Insurance Institution for the Raw Materials and Chemical Industry (BG RCI); German Chemical Industry

Association (VCI), Institute for Occupational Safety and Health of the DGUV (IFA); Research Group Mechanical Process Engineering, Institute of Process Engineering and Environmental Technology, Technical University Dresden (TUD), August, Germany

US EPA (2013), Office of Solid Waste; *Municipal Solid Waste in the United States: 2011 Facts and Figures*, US EPA, Washington DC, 2013;
www.epa.gov/osw/nonhaz/municipal/msw99.htm

VCI/BAuA (2012), Association of the German Chemical Industry (VCI)/ German Federal Institute for Occupational Safety and Health (BAuA), *Guidance for Handling and Use of Nanomaterials at the Workplace*, Frankfurt/Berlin

VCI (2012), Association of the German Chemical Industry (VCI), *Guidance for the Safe Recovery and Disposal of Wastes containing Nanomaterials*, Frankfurt a. M.

VDI (2004), Luther, W. (ed.), *Industrial application of nanomaterials - chances and risks*, VDI Technologiezentrum, Dusseldorf;
www.vditz.de/publikation/industrial-application-of-nanomaterials-chances-and-risks/